



DATA SHEET

Filter media
Blended 80/20

Blended 80/20

Appearance	White, corrugated
Use	Pleatable filter media
Composition	Blended Cellulose + Synthetic
Area weight	130 g/m ²
Thickness	0.35 mm
Air Permeability (Frazier)	540 m ³ /m ² .h at 125 Pa
IFA/BIA certificate (DIN 660335-2-69)	Class M Test report number: 201723219/6120
Temperature (dry heat)	
Continuous	65 °C
Peaks	80 °C
Chemical resistance	
Hydrolysis	N/A
Acids	Poor
Alkalis	Fair
Oxidising agents	Poor
Organic solvents	Fair
Abrasion resistance	Good
Supports combustion	Yes
Application field	Fine dust fumes caused by laser and plasma cutting, welding fumes, shot blasting.